

Datasheet

Dimensions

Characteristic	Method	Units	Value
Length	EN 1848-2	m	6 ± 1%
Width	EN 1848-2	m	150 – 1000
Thickness	EN 1849-2	mm	3,0 ± 0,2
Mass	EN 1849-2	kg/m ²	3,85 ± 10%
Dimensional stability	EN 1107-2	%	0,0

Functional properties

Characteristic	Method	Units	Value
Water tightness	EN 1928-B	kPa	≥ 500
Water absorption	M.O.A.T 66	%	1,06
Water tightness of joint (hot air) 10 kPa	M.O.A.T27		pass
Water tightness (after 2400 hrs UVB test)	EN 1928-B	kPa	≥ 500
Water Vapour Transmission	EN 1931	g	5,26.10 ⁻⁸ kg.m ⁻² .s ⁻¹
Water Vapour Transmission after thermal ageing	EN 1296 + EN 1931	g	5,20.10 ⁻⁸ kg.m ⁻² .s ⁻¹

Mechanical properties

Characteristic	Method	Units	Value
Tensile properties:			
Maximum tensile force length direction	EN 12311-2	N/50 mm	500 ± 50
Maximum tensile force width direction	EN 12311-2	N/50 mm	1000 ± 50
Elongation at break length direction	EN 12311-2	%	80 ± 20
Elongation at break width direction	EN 12311-2	%	15 ± 5
Tear resistance length direction	EN 12310-1	N	400 ± 50
Tear resistance width direction	EN 12310-1	N	400 ± 50
Static loading (method B)	EN 12730	kg	≥ 20
Impact resistance (method B)	EN 12691	mm	≥ 2000
Hail resistance (hard support)	EN 13583	m s ⁻¹	44
Resistance to peel (concrete)	M.O.A.T 66	N/50 mm	162
Resistance to peel (concrete) after thermal ageing at 80 °C, 12 weeks	M.O.A.T 66	N/50 mm	143
Low temperature foldability	EN 495-5	°C	≤ -70
Low temperature foldability after thermal ageing at 80 °C, 12 weeks	EN 495-5	°C	≤ -70

Datasheet

Joint strength (Leadax Sealant)			
Characteristic	Method	Units	Value
Peel resistance:			
Length direction	EN 12316-2	N/50mm	≥ 200
Width direction	EN 12316-2	N/50mm	≥ 200
Shear resistance:			
Length direction	EN 12317-2	N/50mm	≥ 450
Width direction	EN 12317-2	N/50mm	≥ 950

Joint strength (Hot Air)			
Characteristic	Method	Units	Value
Peel resistance:			
Length direction	EN 12316-2	N/50mm	≥ 300
Width direction	EN 12316-2	N/50mm	≥ 400
Shear resistance:			
Length direction	EN 12317-2	N/50mm	≥ 500
Width direction	EN 12317-2	N/50mm	≥ 1200

Fire behaviour			
Characteristic	Method	Units	Value
Reaction to Fire	EN 13501-1		E
Spread of Flame	BS 476-3		C

Compatibility			
Characteristic	Method	Units	Value
Compatibility with bitumen	BRL 1511-1		Pass
Compatibility with PVC	BRL 1511-1		Pass

Chemical resistance			
Characteristic	Method	Units	Value
Chemical resistance to lime milk (Ca(OH) ₂)	EN 1847		Pass